

ARCHITECTURAL AND RESIDENTIAL BRICK



<p>Modular</p> <p>Weight: 3.8 lbs Brick/Sq Ft (3/8 joint): 6.86</p>	<p>Standard</p> <p>Weight: 4.2 lbs Brick/Sq Ft (3/8 joint): 6.67</p>	<p>Queensize</p> <p>Weight: 3.7 lbs Brick/Sq Ft (3/8 joint): 5.65</p>	<p>Engineer</p> <p>Weight: 4.7 Brick/Sq Ft (3/8 joint): 5.65</p>
<p>Builders Special</p> <p>Weight: 4.3 lbs Brick/Sq Ft (3/8 joint): 5.02</p>	<p>Kingsize</p> <p>Weight: 4.4 lbs Brick/Sq Ft (3/8 joint): 4.80</p>	<p>Norman</p> <p>Weight: 6.0 lbs Brick/Sq Ft (3/8 joint): 4.50</p>	<p>Triple Brick</p> <p>Weight: 12.1 Brick/Sq Ft (3/8 joint): 2.25</p>
<p>8" Utility</p> <p>Weight: 6.1 lbs Brick/Sq Ft (3/8 joint): 4.5</p>	<p>12" Utility</p> <p>Weight: 9.1 lbs Brick/Sq Ft (3/8 joint): 3.0</p>	<p>Pavers</p> <p>Weight: 5.8 lbs Brick/Sq Ft (3/8 joint): 4.50*</p>	<p>*Pavers laid without mortar</p>

Mortar Type	Mortar Mixes & Quantities	Portland Cement	Masonry Cement	Hydrated Lime	Sand
M	High compressive strength and somewhat greater durability. For unreinforced masonry below grade and in contact with earth, such as foundations, retaining walls, walks, sewers, and manholes.	1.00 1.00	- 1.00	.25 -	3.75 6.00
S	High tensile bond strength with reasonably high compressive strength. For reinforced and unreinforced masonry for maximum flexural strength and where mortar adhesion is the sole bonding agent.	1.00 .05	- 1.00	.50 -	4.50 4.50
N	Medium strength for general use in exposed masonry above grade. For parapet walls, chimneys, and exterior walls subject to severe exposure.	1.00 -	- 1.00	1.00 -	6.00 3.00

Specification Data

The face brick in this brochure meet the following ASTM Specifications: C-216 Facing Brick, C-652 Hollow Brick

The Pavers in this brochure meet the following ASTM Specifications: C-902 Pedestrian and Light Traffic, C-410 Industrial Floor Brick

We also sell a wide variety of special shapes and sizes manufactured to architect's designs and specifications.

The sizes shown are not standard manufacture for all brick colors or manufacturing locations. Final color selections should be made from actual brick samples.

YOUR MASONRY LANDSCAPE SOURCE



King's Material, Inc · Cedar Rapids · Coralville · Eldridge · www.kingsmaterial.com
Marquart Concrete Products · Clear Lake · Marshalltown · Waterloo · www.marquartconcreteproducts.com

© 2013 King's Material, Inc.
All Rights Reserved